

IKOpro SOLVENT FREE WATERPROOFER

PRODUCT INFORMATION

IKOpro Solvent Free Waterproofer is an easy to use bitumen based emulsion for roofs. The product can be used as a waterproofing coating on asphalt, fibre cement sheeting, concrete, and bituminous roofing membranes.

Size	Product Code
2.5L	MW941802
5L	MW941805

USE

A bitumen based roof emulsion for the purpose of general maintenance and extending the life of an existing waterproofing or roofing system.

FEATURES & BENEFITS

Ease of Use - brush or roller application.

PERFORMANCE & COMPOSITION

Composition:	Bitumen Emulsion
Form:	Liquid
Colour:	Black
General Dimension Data	
Unit size:	22.5 Litres
Coverage Rate*:	1.5m ² /litre/coat (0.67L/m ² /coat)
Application Temperature:	
Surface	5°C and rising
Drying Times**:	24 hours

* Subject to surface porosity

** Depending upon external conditions

DIRECTIONS FOR USE

MATERIAL HANDLING

For specific storage and handling requirements, please refer to relevant sections of the IKO Safety Data Sheet.

SURFACE PREPARATION

All surfaces must be clean, dry and free from grease, oil, dirt and loose material. The area should also be swept to remove all loose chippings. Treat and remove any algae and fungi using IKOpro Algae and Fungi Remover.

Any blisters and cracks present in the existing roof surface should be repaired using IKOpro Emergency Roof Repair Compound. Splits larger than 10mm wide may require additional reinforcement with an appropriate material.

All surfaces once prepared should be primed using IKOpro Quick Drying Primer and allowed to dry.

APPLICATION

Apply a minimum of 2 coats of IKOpro Solvent Free Waterproofer with a brush or roller at the coverage rates prescribed. Each coat must be allowed to dry for at least 24 hours before applying the next.

This product has a 24 hour drying period and must not be used when rain or freezing conditions are forecast during this period.

CLEANING

Brushes and tools can be cleaned with white spirit.

DISPOSAL

For specific disposal of waste, unused and contaminated packaging, please refer to relevant sections of the IKO Safety Data Sheet.

DISCLAIMER

Whilst every precaution is taken to ensure that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded.

IKO reserve the right to amend and/or withdraw this document without notice. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification, application details, withdrawals or otherwise have taken place since this literature was issued.