# **Calder Lead Sheet Sealant**

## **Product description**

Calder Lead Sheet Sealant is a high quality, neutral, elastic one-component joint sealant based on silicones.

## **Properties**

- Very good adhesion on many materials
- Easy to apply
- · Permanently elastic after curing
- Good UV resistance
- Excellent moisture resistance
- Very good resistance to ageing
- MEKO free
- Not suitable for natural stone
- Not paintable

## **Applications**

- Sealing lead flashing into brick, stone or concrete
- · Joints on gutters, downpipes and venting

#### Technical data

Base	Polysiloxane	
Consistency	Stable paste	
Curing system	Moisture curing	
Skin formation	ca. 6 minutes	
Curing speed	ca. 2 mm/24h	
Density	ca. 1.05 g/ml (transp.)   ca. 1.16 g/ml (colour)	
Maximum allowed distortion	± 20 %	
Elasticity modulus	ISO 37	ca. 0.30 N/mm²
Elastic recovery	ISO 7389	> 80 %
Elongation at break	ISO 37	ca. 700 %
Maximum tension	ISO 37	ca. 1.35 N/mm²
Hardness	ca. 16 ± 5 Shore A	
Application temperature	+5°C → +35°C	
Temperature resistance	-60°C → +120°C	

Footnote: Skinning time and curing speed may vary depending on environmental factors such as temperature, moisture, and type of substrates.

#### **Substrates**

Substrate condition -

Technical datasheet
Calder Lead Sheet Sealant | Master Code: 9910966
Revision: 06-06-2025



Technical datasheet

Page 2 of 3

The surface must be rigid, clean, dry, free of dust and grease.

• Substrate preparation -

Porous surfaces should be primed with Primer 150. If needed non porous surfaces can be prepared with a Soudal activator or cleaner (see Technical Data Sheet).

Substrate types -

Calder Lead Sheet Sealant has a good adhesion to following substrates: all usual building substrates, etc.. Calder Lead Sheet Sealant has no good adhesion or is not suitable for PE, PP, PTFE (Teflon®), bituminous substrates. We recommend a preliminary adhesion and compatibility test on every surface.

#### **Application method**

- Application method -
  - Apply the product with a manual, pneumatic or a caulking gun.
- Cleaning method -
  - Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).
- Finishing method -
  - With Finishing Solution before skinning.
- Repair method Repair with the same material.

## **Health- and Safety Recommendations**

Take the usual labour hygiene into account. Consult the packaging label and safety data sheet for more information. Keep the area well-ventilated during use and curing of the product. Dangerous. Respect the precautions for use.

#### Packaging/Logistics

Colour: Please consult the product catalogue, the website or a representative.

Packaging: Please consult the product catalogue, the website or a representative.

Shelf life: 12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and

+25°C

## Joint dimensions

Min. width for joints: 5 mm
 Max. width for joints: 30 mm
 Min. depth for joints: 5 mm

Recommendation for sealing jobs: joint width = 2 x joint depth

• Three-point adhesion should be avoided at all times. Too small joint dimensions can have the effect that the silicone is pulled off because of too large movements.

#### **Environmental clauses**

Leed regulation: Calder Lead Sheet Sealant conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

#### Remarks

Do not use on natural stones like marble, granite...(staining).



Technical datasheet

Page 3 of 3

- Direct contact with the secondary sealing of insulating glass units (insulation) and the PVB-film of safety glass must be avoided.
- Because of the diversity we recommend doing adhesion tests on aluminium lackers, textured coating and PVC before application.
- In an acid environment or in a dark room, a white sealant can slightly turn yellow. Under the influence of sunlight, it will turn back to its initial colour.
- A total absence of UV can cause a colour change of the sealant.
- When finishing with a finishing- or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore, we recommend to only dip the finishing tool in this solution.
- We strongly recommend not to apply the Finishing Solution in full sunlight as it will dry very fast in these circumstances.
- Do not use on polycarbonate.
- Not suitable for bonding aquariums.
- Do not use in applications where continuous water immersion is possible.
- Discoloration of the product due to chemicals, high temperatures, UV-radiation may occur.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discoloration and loss of adhesion.

This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. It is general in nature and does not constitute any liability. Because of the d1iversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application. In every case it is recommended to carry out preliminary experiments. The manufacturer reserves the right to modify products without prior notice.