

Technical data sheet

T06038 - V01 - 10-2020

ONDULINE®
DURO SX 35

Material / Application

Lightweight bitumen sheet for roofing application on auxiliary buildings.

Bitumen sheet reinforced with cellulosic fibers and thermosetting resin. The composite is colored with inorganic pigments.

CE EN 534:2010 - Corrugated bitumen sheets - Category S.

DOP: 06-002 2016-12-12

Technical characteristics


Length	L	200 cm
Width	w	82 cm
Thickness	t	3.5 mm
Height of corrugation	H	38 mm
Pitch of corrugation	P	96 mm
Product surface		1.64 m ²
Product net surface		1.34 m ²
Weight		6.0 kg
Weight / m ²		3.66 kg/m ²
Corrugations / Flat sections		6 / 5

MECHANICAL & PHYSICAL PROPERTIES

Bending under downward load	> 700 N/m ²
Impact strength	250 mm
Tearing strength	> 150 N
Water impermeability	Pass ¹
Proportion of bitumen	> 40%
Homogeneity	Pass ²
Water absorption	< 20%

¹ No drop of water underneath sheet after 48 hours

² No area larger than 1 cm² without bitumen



DURABILITY

Water impermeability after ageing	Pass ¹
Tearing strength after ageing	> 150 N
Thermal coefficient	< 100.10-6 1/K

FIRE PERFORMANCE

Reaction to fire - EN 13501-1	E
External fire performance - EN 13501-5	Froof

Color



Intense

Anthracite Grey

Intense Red

Classic Red

Forest Green

Installation

Special conditions for proper installation are required. Refer to the installation guide.

- Minimum Pitch = 5°
- Max Overhang = 3,5 cm
- Horizontal overlap = 15 cm
- Side overlap = 9,5 cm
- Minimum Roof structure:

Slope in °	Slope in %	Purlin spacing
> 15°	> 27 %	46 cm
10° < - < 15°	17% < - < 27 %	37 cm
5° < - < 10°	9% < - < 17%	Full Deck (OSB, Plywood...)

To maximize performance and in areas of heavy snow, installation on decking is recommended.

- 15 Onduline screws or nails per sheet (eq. 10 / m²)
- Make sure to fix every corrugation at eave and horizontal overlaps.

onduline.com

Onduline
24, Quai Gallieni
92150 Suresnes, FRANCE

Onduline®
Lightweight roofing systems