

EXPERIMENT NAME	UNIT	TEST TOLERANCE	RESULTS	METHOD
TOTAL THICKNESS	<i>mm</i>	+ 0.13 - 0.10	3,950 – 4,130 mm	ISO 24346
WEAR LAYER THICKNESS	<i>Micron</i>	+ 0.13 % - 0.10 %	300	ISO 24340
GLOSS	<i>GU</i>	4 - 7	6,8 GU	ISO 10582
CHEMICAL RESISTANCE	—	0 - 3	0	ISO 26987
CURLING	<i>mm</i>	≤ 2 mm	0,60 mm	ISO 23999
DIMENSIONAL STABILITY	% AVERAGE	—	% 0,09	ISO 23999
SCOTCH TEST	<i>N/mm²</i>	> 0.30 N	0,6 N	EN 1373
RESIDUAL INDENTATION	<i>mm</i>	≤0,10mm	0,02 mm	ISO 24343-1