



# Technical Data Sheet



Technical Data Sheet  
Ref:US1000  
Issued: 12/05/2025  
Number of pages: 4

## Kitchen & Bathroom Anti-Mould

Mould resistant sanitary silicone sealant  
NO-CUT OPEN PACK

### CHARACTERISTICS

**UniBond Kitchen & Bathroom Anti-Mould** is a high quality one component, ready-to-use, silicone sealant (acetoxy type) which contains a fungicide for general sanitary sealing applications.

- Easy to use and apply – No knife required to open cartridge
- Smooth and glossy appearance
- Flexible – 12.5% movement capability
- Highly durable – 15 year guarantee<sup>#</sup>
- Waterproof
- Primeless adhesion to glass, ceramics, vitreous, painted surfaces and anodized aluminium.
- Resistance to fungal growth
- Good resistance to conventional cleaning products and many chemicals



### APPLICATIONS

**Kitchen & Bathroom Anti-Mould** can be used for:

- sealing baths, sinks, showers, kitchen furniture/ worktops, toilets, urinals.
- sealing ceramic or porcelain tiles, plumbing fixtures or cold rooms

### STANDARDS

BS EN 15651-3	product type S: sealant for sanitary applications
BS EN 15301-1	reaction to fire: class E
ISO 846-B	microbiological growth: level 0
ISO 1600	Class F-12.5E

<sup>#</sup>Guarantee is limited to refund of product cost. This does not affect your statutory rights.



## TECHNICAL DATA

<b>Before curing</b>	
Type of silicone	Acetoxy
Appearance	Paste
Density (ISO 2811-1)	~ 0,99 g/ml
Resistance to flow (ISO 7390)	~ 0 mm

<b>Curing</b>	
Skin formation time(+23 °C / 50% RH)	~ 20 min.
Curing speed (+23°C, 50% RH, cross-section of joint 20x10mm)	~ 2 mm / day
Application temperature	+ 5°C to + 40°C

<b>After curing</b>	
Shore A hardness (ISO 868)	~ 20
Movement capability (ISO 11600)	12.5%
Max. joint width	30 mm
Change of volume (ISO 10563)	~ 20%
Temperature Resistance	- 30°C to + 120°C

<b>Mechanical properties</b>	
Elastic recovery (ISO 7389-A)	~ 95%
Modulus at 100% elongation (ISO 8339-A)	~ 0.4 N/mm <sup>2</sup>
Elongation at break (ISO 8339-A)	~ 100%

## INSTRUCTIONS FOR USE

### Note:

- Cartridge gun required
- No knife required to open cartridge!





**UniBond Kitchen & Bathroom Anti-Mould** is supplied ready-to-use and can be applied from the original packaging with no special pre-treatment.

### **Surface preparation**

All surfaces must be clean and dry, free from dust and grease or, anything which may be detrimental to correct adhesion of the sealant.

Residues of old sealant or other materials as well as mould on the substrate must be removed completely (if necessary, use a silicone remover).

### **Joint dimensions**

The movement capability of the sealant as well as local regulations must be considered.

In general, the joint width must be > 10mm and < 35mm and the joint width should be twice the depth.

In the case of deep joints, fill with PE foam 'Backer Rod' prior to applying the sealant.

In case of rectangular sanitary joints, it is necessary to maintain a minimal depth of 5mm.

In case of triangular joints, both contact areas should be minimum 5mm wide.

### **Sealant application**

The sealant should be applied ensuring that the seal is filled. Smoothing off the seal ensures good contact between the sealant and the bonding surfaces.

Directly after application, smooth off with an Unibond sealant smoother tool.

Remove any tape immediately, before surface skin has formed on the sealant.

Smooth over any proud sealant edges immediately.

**Coverage:** Approx 11m using a 5mm bead

### **Cleaning tools/ Excess sealant**

Fresh sealant may be cleaned with a cloth soaked in white spirit or alcohol (e.g., methylated spirit)

Cured sealant can be removed by scraping (e. g. using a razor blade) or by using a special silicone remover product.

### **Drying time**

The sealant will be touch dry in approx. 20 mins and fully dry in approx. 24 hours\*

*\*Curing speed is dependent on temperature, air humidity and on the dimensions of the joint. Low temperatures, high air humidity or big joint dimensions require longer curing times.*

### **Please note**

The joint must be cleaned and maintained regularly.

Ensure good ventilation in the room where the sealant is applied.

### **LIMITATIONS**

Must not be used on sensitive surfaces which could react with the acetic acid which is released during cure.

Not recommended for structural glazing applications.

Not recommended for joints that are in direct food contact.

Not recommended for swimming pool joints, for aquarium joints or for applications under water.

Cannot be over-painted.



Before using on painted substrates, paint must be completely dry and cured. Prior compatibility tests are recommended, considering the variety of paints that exist.

Not recommended on materials which can exude certain components over time (butyl sealant, EPDM rubbers, polychloroprenes, etc.). Discolouration or reduction of adhesion properties could take place.

Do not apply to natural stone. For natural stone, use a neutral curing sealant suitable for natural stone.

Not recommended for applications on PTFE (Teflon®), polypropylene or polyethylene.

For any applications on sensitive surfaces carry out preliminary testing to check compatibility with the sealant.

## GENERAL INFORMATION

### Storage

Store in a cool, dry place between +5 °C and +25 °C. Shelf life is 24 months in an unopened cartridge after date of manufacture (the expiry date is shown on the packaging).

### Colours

Translucent, White, Grey

### Packaging

<b>Description</b>	"No-Cut" opening plastic and cardboard cartridge. The sealant is contained within an internal foil-laminated 'sausage' pouch for secure and efficient storage
<b>Volume Fill</b>	280ml
<b>Net Weight</b>	274g
<b>Gross Weight</b>	336g
<b>Height</b>	249mm
<b>Diameter</b>	50mm
<b>Recycled content</b>	Minimum 67%

## HEALTH AND SAFETY

Before using the product, please see related Material Safety Data Sheet that is available to download from [mymds.henkel.com](http://mymds.henkel.com).

"The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. f.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law."

### Henkel Limited

Wood Lane End, Hemel Hempstead, Hertfordshire, HP2 4RQ

Phone: +44 (0) 1606 593 933

Internet: [www.henkel.co.uk](http://www.henkel.co.uk)



email: [technical.services@henkel.co.uk](mailto:technical.services@henkel.co.uk)